

# ANHUI SINOGRACE CHEMICAL

## 60/40 Hybrid polyester resin for powder coating

Type	Acid value (mgKOH/g)	Viscosity (mpa.s, 200 °C)	Tg (°C)	Curing (°C/min)	Features	Note
SG6011	45~55	2000~4000	≥53	180/15	General purpose, impact resistance, good leveling	
SG6011N	45~55	2000~4000	≥53	180/15	Organotin free, eco-friendly	
SG6012	45~55	4500~6500	≥53	180~190/15	Matted special resin, excellent mechanical property	
SG6015	45~55	4000~7000	≥52	180/15	Textured polyester resin	
SG6016	45~55	2500~3500	≥51	180/15	Ultra low cost general polyester resin	
SG6018	45~55	2500~3500	≥53	180/10	High gloss, high leveling and general purpose	
SG6200	48~55	1500~4500	≥52	180/15	Excellent mechanical, leveling and anti-yellowing properties	Baking resistant type
SG6211	48~55	2000~3500	≥53	180/10	High gloss, high leveling and excellent mechanical properties	
SG6600	45~55	2500~3500	≥55	180/15	High gloss, high leveling and comprehensive properties	
SG6611	45~55	5500~8500	≥56	180/10~15	High gloss, boiling water resistance and excellent mechanical properties	Gas oven
SG6700	48~55	3000~5000	≥53	160/15 140/30	Low curing temperature, excellent mechanical and good leveling properties	
SG6701	48~55	1500~3000	≥52	160/15~20	Low curing temperature, high gloss and good leveling properties	
SG6800	45~55	3000~6000	≥61	180/15	High Tg, excellent mechanical properties and comprehensive performance	

**CONTACT US**

**Jack Tao**

**Export Director**

**Mob:+86-15855525589**

**Email: [sales@sinogracechem.com](mailto:sales@sinogracechem.com)**

**Anhui Sinograce Chemical Co., Ltd.**

**Add: Suite 1116-1117, Block C, Feixi Road, Shushan District, Hefei city, Anhui province,  
China**

**Tel:+86-551-63459511/Fax:+86-551-63668835**

**Web: [www.sinogracechem.com](http://www.sinogracechem.com)**